

## ABSTRACT OF THE DISCLOSURE

A fuse for an automobile having a housing manufactured by the injection molding of a polyamide resin composition, wherein the polyamide resin composition constituting the housing has a heat of fusion of 40J/g or more, as measured by means of a differential scanning calorimeter, and exhibits an average diameter of spherulites of 0.5 $\mu$ m or less, as measured by the observation by means of a polarization optical microscope.